

# DECIABLANK

Versione 1.1.0 - 2023

### **DESCRIPTION**

White pigmented fixative sealer. Its application evens out the absorption of substrates and facilitates subsequent coats of finish. Based on aqueous emulsions, it is suitable for old, new surfaces and plasterboard. DECIABLANK is characterized by high coverage, opacity and filler.

### PHYSICAL CHEMICAL CHARACTERISTICS

COLOR white ASPECT liquid

**COMPOSITION** binder based on aqueous emulsions.

SPECIFIC WEIGHT  $1.30 \pm 0.05$  g/cm3 at 20 °C VISCOSITY  $3200 \pm 1000$  cps R6 rpm 60

Note: These properties are typical ones and are not to be considered specific. Marginal deviations in the values do not affect the effectiveness or properties of the product.

# **APPLICATION CHARACTERISTICS**

TEMP. OF APPLICATION between +5 and +25 degrees °C

DRYING 3-5 hours (referred to 20°C and 65% R.H.)

YIELD 9-12 m2 /l depending on substrate

DILUTION 30-40% with potable water depending on the substrate

APPLICATION EQUIPMENT brush - roller

# **APPLICATION SYSTEM**

**SUPPORTS:** interior masonry work

**SUBSTRATE PREPARATION:** The substrate must be sound, dry, clean, free of salt efflorescence, and free of moisture stains and mold. Old chalking paints should be removed by pressure washing. Do not apply to fresh or particularly alkaline substrates; observe a minimum carbonation period of at least four weeks. Imperfections, cracks, will have to be restored using MURAPLASTER.

Note: Successful application cycles are conditioned by proper preparation of the substrate. What is described in the sheet represents a minimum condition that should be supplemented to the professionalism and experience of the operator.

## **APPLICATION CYCLE**

**NEW PLASTERS** apply one coat of DECIABLANK suitably diluted

with potable water, complete the cycle with the most suitable finish.

**OLD PLASTERS** see "PREPARATION OF THE SUBSTRATE." Proceed with the

finishing as for "NEW PLASTERS."

**NOTE** mix well before use.

#### SPECIFICATION ITEM

GENERAL FEATURES SPECIFIC WEIGHT

pigmented fixative based on aqueous emulsions.

 $1.30 \pm 0.05$  g/cm3 at 20 °C.

## **PACKAGING**

**PACKAGING** plastic buckets lt 14 - 5 - 2.5 - 0.75

#### **GENERAL NOTES**

The product is sensitive to frost. It is recommended, to store it at temperatures between +5° and +25°C. Stored in the original tightly closed packages, and undiluted with water, it has a medium storage period. Avoid application to fresh or particularly alkaline substrates, observing a minimum period of at least four weeks.

Use potable water for dilution and maintain the same proportions throughout application.

All of the above technical information contained within this sheet is the result of careful laboratory tests and practical experience. They do not represent a legal warranty, expressed or implied, about the use of our product as used outside of our control. Each user should verify the effectiveness and behavior of our product with regard to its specific applications.