

## DESCRIPTION

Lime-based paste mineral coating. Designed to adhere and obtain the best results on lime-based substrates called "old mortars." Its high breathability and remarkable resistance to atmospheric agents make it particularly suitable in the restoration of old finishes in historic centers.

## PHYSICAL CHEMICAL CHARACTERISTICS

<b>COLOR</b>	white
<b>APPEARANCE</b>	matt
<b>COMPOSITION</b>	lime putty and selected aggregates
<b>SPECIFIC WEIGHT</b>	1.55 ± 0.1 g/cm <sup>3</sup> at 20 °C
<b>VISCOSITY</b>	paste
<b>GRANULOMETRY</b>	fine medium
<b>PERMEABILITY</b>	high

Note: These properties are typical ones and are not to be considered specific. Marginal deviations of the values do not affect the efficacy or property of the product.

## APPLICATION CHARACTERISTICS

<b>TEMP. OF APPLICATION</b>	between +5 and +25 degrees °C
<b>DRYING</b>	8-24 hours (referred to 20°C and 65% R.H.)
<b>YIELD</b>	3-4 kg/m <sup>2</sup> two coats (fine) 4-5 kg/m <sup>2</sup> two coats (medium)
<b>DILUTION</b>	ready to use
<b>EQUIPMENT</b>	spatula

## APPLICATION SYSTEM

**SUBSTRATES:** lime-based plaster, lime-based gauged mortar.

**SUBSTRATE PREPARATION:** The substrate must be sound, dry and clean, free of salt efflorescence, and free of moisture stains and mold. Old chalking paints should be removed by brushing or pressure washing. Do not apply to fresh or particularly alkaline substrates; observe a minimum carbonation period of at least four weeks. Substrates must be always moistened before applying the product. Imperfections, cracks, will have to be restored using RASATURA DI BASE.

Note: Successful application cycles are conditioned by proper preparation of the substrate. What is described in the sheet represents a minimum condition that should be supplemented to the professionalism and experience of the operator.

## **APPLICATION CYCLE**

**NEW PLASTERS** adequately moisten the substrate with water before applying LA VECCHIA CALCE INTONACO.

**OLD PLASTERS** see "PREPARATION OF THE SUBSTRATE." Proceed with the finishing as for the "NEW PLASTERS."

**NOTE** the coating acquires all its properties after ten days approximately

## **SPECIFICATION ITEM**

**GENERAL CHARACTERISTICS** slaked lime and selected aggregates  
**SPECIFIC WEIGHT** 1.55 ± 0.1 g/cm<sup>3</sup> at 20 °C

## **PACKAGING**

**PACKAGING** plastic buckets kg 25

## **GENERAL NOTES.**

The product is sensitive to frost. It is recommended, that it be stored at temperatures between +5° and +25°C. Stored in the original tightly closed packages, and not diluted with water, it has a medium storage period.

Product tintable with inorganic pigments in paste form. The same tint reproduced in different batches may show color variations, as well as the same batch, applied several days apart or under different environmental conditions.

Do not apply in rain, strong wind, under direct sunlight. Protect surfaces from heavy rain for at least 48 hours after application. Avoid application to too large an area by marking off the working area with adhesive paper tapes. Remove adhesive tapes while the product is still wet. Use potable water for dilution and maintain the same proportions throughout application. The product is caustic, so protect glass, metal parts, stones and anything else that may come in contact with it.

All of the above technical information contained within this sheet, is the result of careful laboratory tests and practical experience. They do not represent a legal warranty, expressed or implied, about the use of our product as used outside of our control. Each user should verify the effectiveness and behavior of our product with regard to its specific applications.