



# DECIASHEEN

Version 1.0.1 - 2024

## DESCRIPTION

Uniforming superwashable with very high coverage. Excellent whiteness, low dirt pick-up and excellent washability. Easy to apply with anti-spatter characteristics. Excellent coverage, filling and masking power make DECIASHEEN a one-coat product, even more so when applied without dilution.

## PHYSICAL CHEMICAL CHARACTERISTICS

<b>COLOR</b>	white
<b>APPEARANCE</b>	matt
<b>COMPOSITION</b>	binder based on aqueous emulsions.
<b>SPECIFIC WEIGHT</b>	1.60 ± 0.05 g/cm <sup>3</sup> at 20 °C
<b>VISCOSITY</b>	7000 ± 1000 cps R6 rpm 60

Note: These properties are typical ones and are not to be considered specific. Marginal deviations in the values do not affect the effectiveness or properties of the product.

## ACCORDING TO UNI EN 13300

<b>HIDING POWER</b>	class 1 (method: contrast ratio for a yield of 4.5 m <sup>2</sup> /l)
<b>WET ABRASION</b>	class 1

## APPLICATION CHARACTERISTICS

<b>TEMP. OF APPLICATION</b>	between +5 and +25 degrees °C
<b>DRYING</b>	3-5 hours (referred to 20°C and 65% R.H.)
<b>YIELD</b>	9 m <sup>2</sup> /l per coat depending on substrate
<b>DILUTION</b>	max. 5% with potable water depending on substrate

**APPLICATION EQUIPMENT** brush - roller - airless

## APPLICATION SYSTEM

**SUPPORTS:** interior masonry work. Especially suitable for gypsum and plasterboard.

**SUBSTRATE PREPARATION:** The substrate must be sound, dry, clean, free of salt efflorescence, and free of moisture stains and mold. Old chalking paints should be removed by pressure washing. Do not apply to fresh or particularly alkaline substrates; observe a minimum carbonation period of at least four weeks. Imperfections, cracks, i shall be restored using MURAPLASTER.

Note: Successful application cycles are conditioned by proper preparation of the substrate. What is described in the sheet represents a minimum condition that should be supplemented to the professionalism and experience of the operator.

## **APPLICATION CYCLE**

**NEW PLASTERS** applicable directly on all substrates without the use of fixative.

**OLD PLASTERS** see "SUBSTRATE PREPARATION." Proceed with the finishing as for "NEW PLASTERS."

**NOTE** mix well before use.

## **SPECIFICATION ITEM**

**GENERAL CHARACTERISTICS** uniforming water paint  
**SPECIFIC WEIGHT** 1.60 ± 0.05 g/cm<sup>3</sup> at 20 °C

## **PACKAGING**

**PACKAGING** plastic buckets lt 14 - 5

## **GENERAL NOTES.**

The product is sensitive to frost. It is recommended, to store it at temperatures between +5° and +25°C. Stored in the original tightly closed packages, and not diluted with water, it has a medium storage period. Avoid application to fresh or particularly alkaline substrates, observing a minimum period of at least four weeks.

Use potable water for dilution and maintain the same proportions throughout application.

All of the above technical information contained within this sheet is the result of careful laboratory tests and practical experience. They do not represent a legal warranty, expressed or implied, about the use of our product as used outside of our control. Each user should verify the effectiveness and behavior of our product with regard to its specific applications.