

## DESCRIPTION

Breathable ultra-fine water-based wall paint for interiors. Vinyl resin-based product of excellent coverage and excellent whiteness. It is recommended for all environments subject to moisture, such as bathrooms and kitchens. Easy to apply and excellent dry rub resistance. Especially suitable for smooth or gypsum-based surfaces, it ensures a pleasant velvety matte appearance.

## PHYSICAL CHEMICAL CHARACTERISTICS

<b>COLOR</b>	white
<b>ASPECT</b>	matte
<b>COMPOSITION</b>	Emulsion copolymer binder
<b>SPECIFIC WEIGHT.</b>	1.68 ± 0.05 g/cm <sup>3</sup> at 20 °C
<b>VISCOSITY</b>	7100 ± 1000 cps R6 rpm 60
<b>DRY RESIDUAL</b>	68 ± 1%
<b>STEAM PERMEABILITY</b>	high
<b>DIRT PICK UP</b>	medium

Note: These properties are typical ones and are not to be considered specific. Marginal deviations of the values do not affect the efficacy or property of the product.

## ACCORDING TO UNI EN 13300

**HIDING POWER** class 1 (method: contrast ratio for a yield of 3.5 m<sup>2</sup> /l)

## APPLICATION CHARACTERISTICS

<b>TEMP. APPLICATION.</b>	between +5 and +32 degrees °C
<b>DRYING</b>	6-8 hours (reported at 20°C and 65% R.H.)
<b>YIELD</b>	7 m <sup>2</sup> /l per coat depending on substrate
<b>DILUTION</b>	1 <sup>st</sup> hand 30-35% drinking water 2 <sup>nd</sup> hand 25-30% drinking water
<b>EQUIPMENT</b>	brush - roller - spray

## APPLICATION SYSTEM

**SUBSTRATES:** civil plaster, stucco shaved walls, plasterboard, fiber cement.

**SUBSTRATE PREPARATION:** The substrate must be sound, dry, clean and free of moisture stains and mold. Old flaking paint should be removed by brushing or sanding. Imperfections, cracks, flaking should be restored using MURAPLASTER.

Note: Successful application cycles are conditioned by proper preparation of the substrate. What is described in the sheet represents a minimum condition that should be supplemented to the professionalism and experience of the operator.

## **APPLICATION CYCLE**

### **NEW PLASTERS.**

apply a coat of ISOLACRIL suitably diluted with drinking water, complete with two coats of MATT with an interval of 4-5 hours from each other

### **OLD PLASTERS**

see "**SUPPORT PREPARATION.**" Proceed to the finish as for "**NEW PLASTERS**"

## **SPECIFICATION ITEM**

### **GENERAL CHARACTERISTICS**

White breathable interior **paint**

### **DRY RESIDUAL**

68 ± 1%

### **SPECIFIC WEIGHT**

1.68 ± 0.05 g/cm<sup>3</sup> at 20 °C

## **PACKAGING**

### **PACKAGING**

plastic buckets lt 14 - 5

## **GENERAL NOTES.**

The product is sensitive to frost. It is recommended, to be stored at a temperature between +5° and +25°C. Stored in the original tightly closed packages, and undiluted with water, it has a long storage period.

Product tintable with organic and inorganic pigments in paste form. It is recommended not to exceed 1 percent by weight of paste, so as not to change the typical breathable properties of the product, and to avoid flaming of the product.

All of the above technical information contained within this sheet is the result of careful laboratory tests and practical experience. They do not represent a legal warranty, expressed or implied, about the use of our product as used outside of our control. Each user should verify the effectiveness and behavior of our product with regard to its specific applications.